

STONBLEND® GSI SAT

PRODUCT DESCRIPTION

Stonblend GSI is a nominal 5mm colored aggregate/resin mortar flooring system that offers a cost-effective alternative to terazzo. It combines decorative looks with excellent chemical and wear resistance and cleanability. Its surface provides a moderate degree of slip resistance while remaining resistant to staining, marring, and yellowing. It is comprised of:

Primer

Stonprime 786 OPR

Stonblend GSI Mortar, 9661

A three-component, troweled mortar consisting of epoxy resin, curing agent and coloured quartz silica aggregate.

Stonblend 967 Grout Coat

A two-component, clear, UV resistant epoxy sealer.

Stonseal GS7 Clear Matt

A two-component, non-reflective, waterborne, aliphatic polyurethane coating. NOTE: Staining may occur depending on length of exposure time, chemical concentration and temperature.

USES, APPLICATIONS

Applications vary from light manufacturing, such as food and pharmaceutical processing, to laboratories, hallways, offices and holding areas in healthcare, educational and correctional facilities. It's easy to maintain, low gloss finish adds to Stonblend GSI's appeal wherever functional, attractive flooring is required.

SUBSTRATE

Stonblend GSI, in conjunction with its appropriate primer, is suitable for application over properly prepared concrete. Not recommended for use over asphalt, mastic, gypsum based products, brick or painted surfaces. These must first be removed by mechanical means to expose the substrate prior to priming and overlayment.

OPTIONS

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 15cm are available.

Smooth Finish

An additional layer of Stonseal 787 Sealer, applied over the cured grout coat, may be added to produce a very smooth finish.

TYPICAL PROPERTIES AT 25°C

Compressive Strength42 MPa after 7 days (ASTM C-579)
Tensile Strength10 MPa (ASTM D-638)
Flexural Strength15 MPa (ASTM C-580)
Flexural Modulus of Elasticity	3.4 MPa (ASTM C-580)
Hardness85 to 90 (ASTM D-2240, Shore D)
Bond Strength	> 1.7 MPa (ASTM D-2240, Shore D)
Impact Resistance	> 17 Joules (ASTM D-2794)
Abrasion Resistance06 mg max weight loss (ASTM D-4060, CS-17)
Slip Index085 (ASTM F-1679)
FlammabilitySelf Extinguishing (ASTM D-635)
Thermal Coefficient of	Extent of burning 0.25 in max Linear Expansion (ASTM C-531)
Water Absorption3 x 10 ⁻⁵ mm/mm/°C .02% (ASTM D-2369)
VOC Content18g/l (ASTM D-2369)
Volume Solids	100%
Heat Resistance Limitations60°C (continuous) 93°C (intermittent spills) (ASTM D-2369)
Cure Rate at 25°C	16 hours for foot traffic 24 Hours for normal operation
ColourRefer to Stonblend colour card

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

PACKAGING AND COVERAGE

Primer, Stonprime 786 O.P.R.

5lt Kit Base + Activator: A, approximately 3-4m²/litre Refer to Stonprime 786 O.P.R. product data sheet\

Mortar, Stonblend GSI 966I

12lt Kit Part A + B + C. Approximately 2,4m²/kit

Grout Coat, Stonblend 967

2lt Kit, Part A + B: Approximately 3m²/kit

Sealer, Stonseal GS7, 968

5lt Kit Part A + B: Approximately 60m²/kit

STORAGE CONDITIONS

Store all components of Stonblend GSI between 16-30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 12 months in the original, unopened container.

COLOUR

Stonblend GSI is available in 12 standard colours. Refer to the Stonblend colour sheet. Custom colours are available upon request.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond. The substrate must be dry and free of all wax, grease, oils, fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles must be removed by mechanical methods, i.e. abrasive blasting or grinding. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent (Carboclean 250 or Carboclean 252) and rinsing with clean water. The surface must show open pores throughout with main aggregate in concrete exposed and have a sandpaper texture. Substrate moisture content prior to coating should be below 5% and substrate tensile strength above 2 MPa. For recommendations or additional information regarding substrate preparation, refer to surface preparation data sheet or contact StonCor Africa Technical Service Department.

PRIMING

The use of Stonprime 786 O.P.R. is necessary for all applications of Stonblend GSI over most substrates. The primer must be tacky during the application of Stonblend GSI. If the primer becomes tack-free, the area must be reprimed prior to continuing the application.

MIXING OF MORTAR

Empty entire contents of Part A (liquid) and Part B (liquid) into a mixing 25lt pail fitted to a JB Blender and mix for 90 seconds.

Pour the entire contents of one bag of Part C aggregate into the rotating pail and mix for a further 90 seconds.

When the blender stops, scrape off excess from mixing blade and remove pail, delivering it to the floor area for application.

APPLICATION

Application of the Stonblend GSI system is accomplished as follows:

Stonblend GSI 966I material is mixed, just prior to use, in accordance with the prescribed directions. The material is then screed applied and trowel finished.

Allow a minimum of 8 hours curing time before applying the Stonblend grout coat, 967.

Stonblend grout coat is applied immediately after mixing. Poured onto the floor in the form of a bead, the liquid is spread over the surface using a squeegee. Once the first coat is finished, apply a second coat immediately over the first coat in a wet-on-wet application. Use a loop roller to remove squeegee lines.

After the grout coat has cured (12 hours minimum), apply the first coat of Stonseal GS7 using a medium nap roller.

After approximately 2 hours, apply a second coat of Stonseal GS7.

Refer to Stonblend GSI Directions for further details

POT LIFE

After mixing, Stonblend GSI has a working time of approximately 20 minutes at 25°C. The working time will vary depending on temperature.

CURING

At normal temperature conditions the coating system can be exposed to light traffic after 24 hours. Excessive traffic, aqueous cleaning and exposure to aggressive chemicals should only take place after four to five days when full cure has been achieved.

REFERENCE SAMPLE

A trial reference sample should be installed by the applicator prior to start of contract to ensure correct coverages and workmanship.

PRECAUTIONS

- May contain flammable solvents. Keep away from sparks and open flames.
- In confined areas, workmen must wear fresh-airline respirators.
- Hypersensitive persons should wear gloves or use protective cream.
- All electronic equipment and installations should be made and grounded in accordance with the National Electrical Code.
- In areas where explosion hazards exists, workmen should be required to use nonferrous tools and to wear conductive and non-sparking shoes.

RECOMMENDATIONS

- DO NOT attempt to install material if the temperature of Stonblend GSI components and substrate are not within 16-30°C. The cure time and application properties of the material are severely affected.

- DO NOT use water or steam in the vicinity of the application. Moisture can seriously affect the working time and other properties.
- The use of NIOSH/MSHA approved respirators and safety glasses are recommended.
- Avoid contact with all liquid Parts A and B as they may cause skin and/or eye irritation. Workmen should cover hands with rubber gloves.
- Use only with adequate ventilation.

NOTES

- Procedures for maintenance of the flooring system are described in the Stonblend Cleaning Procedures.
- Specific information regarding chemical resistance is available in the Stonblend Chemical Resistance Guide.
- Safety Data Sheets for Stonblend GSI are available on request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to our flooring products specifically or flooring problems in general.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.

IMPORTANT:

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact StonCor Africa to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to StonCor Africa quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data, if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY STONCOR AFRICA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Rev. 10/18, © 2018 Stonhard

STONHARD

Worldwide Offices

Africa (27)11.254.5500 | stonhard.co.za
 India (91) 22 28500321 | stonhard.in
 USA 800.257.7953 | stonhard.com

Canada (905)430.3333 | stonhard.ca
 Mexico (52)55.9140.4500 | stonhard.mx
 South America (54-11) 5032 3113 | stonhard.ar

Europe (32) 67.49.37.10 | stonhard.co.uk
 Middle East (971)4.3470460 | stonhard.me
 Asia (86)21.5466.5118 | stonhard.ch